

# MULTYPRO 20/30

## DEFINITION:

High performance multigrade asphalt bitumen.

## SPECIFICATIONS:

Characteristics	Units	Standard	Min.	Max.
<b>Fresh binder</b>				
Penetration (25 °C)	0,1 mm	EN 1426	20	30
Softening point (R&B)	°C	EN 1427	62	72
Penetration index	-	EN 12591	0,0	-
Fraass point	°C	EN 12593	-	-4
Flash point	°C	EN 2592	235	-
<b>RTFOT residue</b>				
Mass loss	%	EN 12607-1	-	0,5
Retained penetration (25°C)	% p.o.	EN 1426	60	-
Increase in softening point	°C	EN 1427	-	8

## APPLICATIONS:

- As a substitute for conventional bitumen in applications requiring improved thermal susceptibility and greater resistance to plastic deformation.

## RECOMMENDED WORKING TEMPERATURES:

- Mixing temperature (°C): 165 - 175.
- Working temperature (°C): 165- 175.
- Compaction temperature (°C): 160- 170.
- Maximum heating temperature (°C): 185.