

# INDUSFALT 100/15

## DEFINITION:

Asphalt bitumen obtained by direct distillation or other refining methods and containing rheology modifiers specially designed to be used as base in industrial products.

## SPECIFICATIONS:

Characteristics	Units	Standard	Min.	Max.
Softening point (R&B)	°C	EN 1427	95	105
Penetration (25°C, 100g, 5s)	0,1 mm	EN 1426	10	20
Solubility in xylene	%	EN 12592	98	-
Mass loss	%	EN 13303	-	0,5
Flash point	°C	EN ISO 2592	250	-

## APPLICATIONS:

- Raw material for waterproofing products in construction and membranes, joint sealing compounds and asphaltic paints.

## RECOMMENDED WORKING TEMPERATURES:

- 110 - 180 °C.