

## INDUSFALT POLIMER

Asphalt bitumen designed for the production of polymer modified bitumen to be used in the manufacture of flexible sheets for waterproofing complying UNE 104-242/1 standard.

### SPECIFICATIONS

Characteristics	Unit	Standard	MIN	MAX
<b>Fresh binder</b>				
Penetration (25°C)	0,1 mm	EN 1426	160	220
Softening point (R&B)	°C	EN 1427	35	43
Fraass point	°C	EN 12593	--	-15
Solubility in xylene	%	EN 12592	99	--
Flash point	°C	EN ISO 2592	220	--
<b>Resistance to hardening at 163°C (EN 12607-1)</b>				
Mass loss	%	EN 12607-1	--	1
Retained penetration	%	EN 1426	37	--
Δ Increase in softening point (R&B)	°C	EN 1427	--	12

### RECOMMENDED WORKING TEMPERATURES

- > Pumping temperature (°C): >100.
- > Polymer modified bitumen manufacture temperature (°C): 170 - 185.